



DERMA-DPC



A DAMP-PROOFING MODIFIED BITUMINOUS MEMBRANE

USES:

DPC COURSE IN BLOCKWORKS, BASEMENTS, ROOFS AND OTHER CIVIL WORKS.

APPLICATION METHOD:

LOOSE LAID / TORCH-ON
TORCHABLE OVERLAPS

SURFACE FINISH :

TOP - PE
BOTTOM - PE

PROPERTY	TYPICAL VALUES	TEST METHOD
Roll Length	10 m	
Roll Width – Available sizes	100mm, 150mm, 200mm, 500mm, 1,000 mm	
Membrane nominal thickness	3 mm	UEAtc
Softening Point of Coating Material	≥ 155 Deg. C.	ASTM D36
Tensile Strength Longitudinal Transverse	280 N/5 cm 200 N/5 cm	ASTM D146,
Elongation Longitudinal Transverse	3.8% 3.9%	ASTM D 412
Reinforcement	50 grms/M2 Fiberglass fleece	UEAtc

DWI, DERMBIT WATERPROOFING INDUSTRIES COMPANY LIMITED
P. O. Box 10308, Jubail Industrial City 31961
Kingdom of Saudi Arabia
Tel.: (00966) 3 3410464
Fax: (00966) 3 3410481
E-mail: dermabit@dermabit.com.sa

Submitted by: